Free Cutting Rephosphorized and Resulfurized Steels

Chemical Composition Ranges and Limits

| SAE No | С | Mn | Р | S |
|--------|----------|----------|---------|---------|
| | | | | |
| 1212 | 0.13 max | .70/1.00 | .07/.12 | .16/.23 |
| | | | | |
| 1213 | .13 max | .70/1.00 | .07/.12 | .24/.33 |
| | | | | |
| 1215 | .09 max | .75/1.05 | .04/.09 | .26/.35 |

hout specified silicon content because of adverse effect on machinability.